



**FBC Chemical Corp.**  
**Asphalt Products Division**

P.O. Box 599  
634 Route 228  
Mars, PA 16046  
(724) 625-3116

**WET/DRY SURFACE ROOF CEMENT**

Item Number: 83150

**PRODUCT DESCRIPTION:** A heavy bodied asphaltic cement for use in cold-process, built-up roofing where a pliable, plastic body waterproof product is required. This product is for use in emergency situations where repairs must be made to wet or damp surfaces. Excellent for patching holes and for flashing around chimneys, downspouts, skylights, vent pipes, gutters, and valleys. Also excellent for sealing cracks in foundations and outside walls. Use on flat or steep roofs made of concrete, felt, metal, and composition.

**SURFACE PREPARATION:** Using stiff brush or broom, remove dirt, debris, loose paint, and other foreign matter. Remove all rust with wire brush; oil and grease with detergents. When applying to uncoated metal, no priming is necessary. For repairs on wet surfaces, shield repair area; create temporary dam to protect from excess water. Soak up surface water with towel as well as possible.

**APPLICATION:** Apply with trowel or putty knife. To patch holes, cracks, or small breaks up to 1/16", fill area to be sealed with wet cement and smooth down edges. To patch larger holes, cracks or breaks, apply wet cement to a thickness of 1/4". Imbed a layer of reinforcing membrane into the wet cement. Apply another 1/4" layer of wet cement over the membrane, feathering the edges. Occasional dipping of trowel in paint thinner will reduce sticking. In cold weather, store cement in heated room for easier workability.

**PACKAGING:** 5 Gallon, 1 Gallon, 1 Quart, 11 oz. Caulking Cartridge

**SPECIFICATIONS:** Meets performance requirements of Federal Specification SS-C-153C, Type 1 – Meets ASTM D4586 (Asbestos-Free) and ASTM D3409.

**CAUTIONS:** **COMBUSTIBLE.** Contains petroleum distillates. Keep away from heat, sparks, and open flame. Use only with adequate ventilation. Avoid prolonged or repeated contact with skin. Avoid breathing of vapors. Do not take internally. **KEEP OUT OF REACH OF CHILDREN.**



**FBC Chemical Corp.**  
**Asphalt Products Division**

P.O. Box 599  
634 Route 228  
Mars, PA 16046  
(724) 625-3116

**WET/DRY SURFACE ROOF CEMENT**

**SPECIFICATIONS**

Meets performance requirements of Federal Specification SS-C-153C, Type 1

Meets ASTM D4586 (Asbestos-Free)

Flash Point.....	105 F
Weight per gallon.....	11 Lbs.
Viscosity @ 80 F. (ASTM D217).....	275-335
Non-Volatile (Federal Test Method 141).....	70% Min.
Percent of specially treated bitumen.....	30% Min.
Percent of total solids, by volume.....	75% Min.
Dry film thickness of 1 gal/15 sq. ft.....	85 mils
Drying time.....	2 to 3 days
Service temperature, extended exposure.....	-20 F to +150 F
Resistance to oils and solvents.....	Poor
Resistance to sunlight and chemicals.....	Good
Effect of weathering.....	Slight chalking
Water resistance:	
Under good drainage conditions.....	Excellent
Under continuous submersion.....	Fair

**CAUTIONS:** COMBUSTIBLE. Contains petroleum distillates. Keep away from heat, sparks and open flame. Use only with adequate ventilation. Avoid prolonged or repeated contact with skin. Avoid breathing of vapors. Do not take internally. **KEEP OUT OF REACH OF CHILDREN.**